

Use Information: This paragraph is informational only and is not exclusively definitive of the end use. For face and back offset printing of file folders, tickets, tags, cards, notices, signs, covers, for books and pads, etc. requiring strength and durability. Printed matter may include text, line illustrations, and solid reverses.

Stock: Free from groundwood pulp.

Note: Not less than 20% postconsumer fiber. Any percent over 20 percentage points, is encouraged, provided that the requirements of this Standard are met.

Basis weight: 24 by 36 inches, 500 sheets
(pounds) 150
A tolerance of $\pm 5\%$ shall be allowed.

Bursting strength: Average not less
than (lb/in²) 100

General appearance: The color, finish, and cleanliness shall conform to the standard sample(s) established by the Government.

Color: The paperboard in the order (or publication) shall be uniform and the color variation shall not exceed DE(CIELAB) = 1.0. Paper shall be manila or match the color sample supplied by the ordering agency. The commercial color standard is applicable, unless specified that the color shall conform to the Government standard. Colors shall not fade and shall appear even and uniform on the surface of the sheet.

Testing: Shall be conducted in accordance with methods in part 2, *Government Paper Specification Standards*. The acceptance criteria Part 4 shall apply.