

## § 27.32

the official color grade. Cotton classers, designated as such by the Director, will determine the official leaf grade and extraneous matter, and authorized Cotton Program employees will determine all fiber property measurements using High Volume Instruments.

[65 FR 36598, June 9, 2000]

### § 27.32 Order of classification.

All cotton for which classifications requests shall be pending shall be classified as far as practicable in the order in which proper samples thereof, ready for such classification, shall have been delivered to the Marketing Services Office, except as otherwise provided in this subpart or when the Area Director or the Director shall find that an emergency exists and shall order otherwise.

[48 FR 49211, Oct. 25, 1983]

### § 27.33 Exposing of samples for classification.

Classification shall not proceed until the samples, after being delivered to the Marketing Services Office, shall have been exposed for such length of time as in the judgment of the Area Director shall be sufficient to put them in proper condition for the purpose.

[48 FR 49211, Oct. 25, 1983]

### § 27.34 Classification procedure.

Classification shall proceed as rapidly as possible, but not when light or other conditions make uncertain the accuracy of the results to be obtained.

### § 27.35 Lower class of two samples to prevail.

In case a sample drawn from one portion of a bale is lower in class than one drawn from another portion of such bale, except as otherwise provided in this subpart, the classification of the bale shall be that of the sample showing the lower class.

### § 27.36 Classification and Micronaire determinations based on official standards.

All cotton shall be classified for grade and staple length on the basis of the official cotton standards of the United States for grade and staple length in effect at the time of such

## 7 CFR Ch. I (1–1–11 Edition)

classification. Micronaire determinations for cotton, upon request under § 27.14, § 27.62, or § 27.63 shall be made according to the official cotton standards of the United States for fiber fineness and maturity in effect at the time of such determinations.

### § 27.37 Cotton reduced in grade.

If cotton be reduced in grade, by reason of the presence of extraneous matter or other irregularities or defects, below its grade according to the official cotton standards of the United States, the grade from which it is so reduced, and the condition or reason which so reduces its grade shall be determined and stated.

[25 FR 5872, June 25, 1960]

### § 27.38 Terms defined for purposes of classification.

For the purposes of classification the following terms shall be construed, respectively, to mean:

(a) *Cotton of perished staple.* Cotton that has the strength of fiber as ordinarily found in cotton destroyed or unduly reduced through exposure to the weather either before picking or after baling, or through heating by fire, or on account of water packing, or by other causes.

(b) [Reserved]

(c) *Gin cut cotton.* Cotton that shows damage in ginning, through cutting by the saws, to an extent that reduces its value more than two grades.

(d) *Reginned cotton.* Cotton that has passed through the ginning process more than once, and cotton that, after having been ginned, has been subjected to a cleaning process and then baled.

(e) *Repacked cotton.* Cotton that is composed of factors', brokers', or other samples, or of loose or miscellaneous lots collected and rebaled, or cotton in a bale which is composed of cotton from two or more smaller bales or parts of bales that are combined after the cotton leaves the gin.

(f) *False packed cotton.* Cotton in a bale (1) containing substances entirely foreign to cotton, (2) containing damaged cotton in the interior with or without any indication of such damage upon the exterior, (3) composed of good cotton upon the exterior and decidedly inferior cotton in the interior, in such