

§ 176.250

21 CFR Ch. I (4-1-13 Edition)

§ 176.250 Poly-1,4,7,10,13-pentaaza-15-hydroxyhexadecane.

Poly-1,4,7,10,13-pentaaza-15-hydroxyhexadecane may be safely used as a retention aid employed prior to the sheet-forming operation in the manufacture of paper and paperboard intended for use in contact with food in an amount not to exceed that necessary to accomplish the intended physical or technical effect and not to exceed 6 pounds per ton of finished paper or paperboard.

§ 176.260 Pulp from reclaimed fiber.

(a) Pulp from reclaimed fiber may be safely used as a component of articles used in producing, manufacturing, packing, processing, preparing, treating, packaging, transporting, or holding food, subject to the provisions of paragraph (b) of this section.

(b) Pulp from reclaimed fiber is prepared from the paper and paperboard products described in paragraphs (b) (1) and (2) of this section, by repulping with water to recover the fiber with the least possible amount of nonfibrous substances.

(1) Industrial waste from the manufacture of paper and paperboard products excluding that which bears or contains any poisonous or deleterious substance which is retained in the recovered pulp and that migrates to the food, except as provided in regulations promulgated under sections 406 and 409 of the Federal Food, Drug, and Cosmetic Act.

(2) Salvage from used paper and paperboard excluding that which (i) bears

or contains any poisonous or deleterious substance which is retained in the recovered pulp and that migrates to the food, except as provided in regulations promulgated under sections 406 and 409 of the act or (ii) has been used for shipping or handling any such substance.

§ 176.300 Slimicides.

(a) Slimicides may be safely used in the manufacture of paper and paperboard that contact food, in accordance with the following prescribed conditions:

(1) Slimicides are used as antimicrobial agents to control slime in the manufacture of paper and paperboard.

(2) Subject to any prescribed limitations, slimicides are prepared from one or more of the slime-control substances named in paragraph (c) of this section to which may be added optional adjuvant substances as provided for under paragraph (d) of this section.

(3) Slimicides are added to the process water used in the production of paper or paperboard, and the quantity added shall not exceed the amount necessary to accomplish the intended technical effect.

(b) To insure safe usage, the label or labeling of slimicides shall bear adequate directions for use.

(c) Slime-control substances permitted for use in the preparation of slimicides include substances subject to prior sanction or approval for such use and the following:

List of substances	Limitations
Acrolein.	
Alkenyl (C ₁₆ -C ₁₈) dimethylethyl-ammonium bromide.	
<i>n</i> -Alkyl (C ₁₂ -C ₁₈) dimethyl benzyl ammonium chloride.	
1,2-Benzisothiazolin-3-one	At a level of 0.06 pound per ton of dry weight fiber.
Bis(1,4-bromoacetoxy)-2-butene.	
5,5-Bis(bromoacetoxymethyl) <i>m</i> -dioxane.	
2,6-Bis(dimethylaminomethyl) cyclohexanone.	
1,2-Bis(monobromoacetoxy) ethane [CA Reg. No. 3785-34-0]	At a maximum level of 0.10 pound per ton of dry weight fiber.
Bis(trichloromethyl)sulfone.	
4-Bromoacetoxymethyl- <i>m</i> -dioxolane.	
2-Bromo-4'-hydroxyacetophenone.	
2-Bromo-2-nitropropane-1,3-diol (CAS Reg. No. 52-51-7)	At a maximum level of 0.6 pound per ton of dry weight fiber.
β-Bromo-β-nitrostyrene	At a maximum level of 1 pound per ton of dry weight fiber.
Chloroethylenebisthiocyanate.	
5-Chloro-2 - methyl - 4 - isothiazolin-3-one calcium chloride and 2-methyl-4-isothiazolin-3-one calcium chloride mixture at a ratio of 3 parts to 1 part.	At a level of 2.5 pounds per ton of dry weight fiber.
Chlorinated levulinic acids.	
Chloromethyl butanethiolsulfonate.	
Cupric nitrate.	